

Armlen PP GF 10-2HS

A 10% glass fibre, light-stabilized polypropylene. This material displays high mechanical and thermal properties. Designed for manufacture of railway dowels, may be applied as a substitution of metals, thermosetting polymers and other thermoplastics in construction, specialty and general items. Available in natural and black colors.

Properties	Test method	Unit	Typical value
MISCELLANEOUS			
Density	ISO 1183	kg/m ³	980
Tensile Strength	ISO 527-1	MPa	54
Strain at Break	ISO 527-1	%	5.6
Flexural Stress at maximum load	ISO 178	MPa	70
Tensile Modulus	ISO 178	MPa	2800
Charpy Impact Strength at +23°C (un-notched)	ISO 179-1	kJ/m ²	38
Charpy Impact Strength at -50°C (un-notched)	ISO 179-1	kJ/m ²	40
THERMAL			
Melting Point	ISO 11357	°C	162
Deflection Temperature at 1.8 MPa load	ISO 75	°C	125
PROCESSING			
Melt Flow Rate (250 °C; 2,16 kg)	ISO 1133	g/10 min	6.8
Melt Temperature		°C	240
Mold Temperature		°C	60
Moulding Shrinkage, parallel	ISO 294-4	%	0.4-0.6
Moulding Shrinkage, normal	ISO 294-4	%	0.7-1.0

Comment:
All processing parameters as well as information on shrinkage specimen should be requested from the manufacturer.
If stored in a dry warehouse – dehydration not required

Date of issue 02.12.2020

The information in this technical description is for reference purposes only. It can be considered as the basis for determining whether material is acceptable for specific applications. Because it is not possible to anticipate all applications of materials and operating conditions, POLYPLASTIC makes no warranty and assumes no liability for the use of the information specified in the catalog. This information may be changed without notice.